



Kodiak[®] “R”

Unbleached high performance uncalendered paper, with the stiffness needed for high conversion rate into multiwall bags. Kodiak “R” is recommended for applications demanding high CD strength and superior converting runnability.

Using premium northern fibres and innovative manufacturing technology, Canfor Pulp Limited Partnership products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C

Nominal Basis Weight (g/m²)

	<i>units of measure</i>	70	80	90	98	105	114	130	<i>Test Method</i>
MD TEA	<i>J/m²</i>	113	130	147	173	186	204	239	ISO 1924-3
CD TEA	<i>J/m²</i>	217	273	286	301	338	357	374	ISO 1924-3
MD TEA Index	<i>J/g</i>	1.6	1.6	1.6	1.8	1.8	1.8	1.8	ISO 1924-3
CD TEA Index	<i>J/g</i>	3.1	3.4	3.2	3.1	3.2	3.1	2.9	ISO 1924-3
MD Tensile	<i>kN/m</i>	7.0	8.1	9.4	10.2	10.7	11.8	12.8	ISO 1924-3
CD Tensile	<i>kN/m</i>	4.6	5.7	6.2	6.6	7.2	8.3	8.0	ISO 1924-3
MD Stretch	<i>%</i>	2.4	2.5	2.5	2.7	2.7	2.7	2.6	ISO 1924-3
CD Stretch	<i>%</i>	7.4	7.4	7.0	6.9	7.1	6.5	6.8	ISO 1924-3
Porosity	<i>s/100mL</i>	18	18	16	17	16	17	18	ISO 5636-5
MD Tear	<i>mN</i>	925	980	1075	1165	1270	1335	1900	ISO 1974
CD Tear	<i>mN</i>	875	935	1055	1195	1275	1370	1800	ISO 1974

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



**Canfor Pulp Limited Partnership
Specialty Paper Group**

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250