



Polar Kraft® R

Bleached, high performance paper, with the stiffness needed for high conversion rates into multiwall bags. Polar "R" is recommended for applications demanding high CD strength and superior converting runnability.

Using premium northern fibres and innovative manufacturing technology, Canfor Pulp Limited Partnership products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment. Canfor Pulp Limited Partnership papers are manufactured in compliance with FDA 21 CFR 176.170 and 176.180, German recommendation XXXVI, CONEG heavy metals and EC directive 94/62/EC. Certificates of compliance to all applicable regulatory requirements will be supplied upon request.

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C

Brightness: 82% ISO

Basis Weight (g/m ²)		80	90	98	Test Method
MD TEA	J/m ²	128	151	174	ISO 1924-3
CD TEA	J/m ²	273	308	325	ISO 1924-3
MD TEA Index	J/g	1.6	1.7	1.8	ISO 1924-3
CD TEA Index	J/g	3.4	3.4	3.3	ISO 1924-3
MD Tensile	kN/m	7.7	9.2	8.8	ISO 1924-3
CD Tensile	kN/m	4.7	6.2	5.8	ISO 1924-3
MD Stretch	%	2.6	2.6	3.2	ISO 1924-3
CD Stretch	%	8.7	7.8	8.4	ISO 1924-3
Porosity	s/100mL	18	18	18	ISO 5636-5
MD Tear	mN	1025	1135	1305	ISO 1974
CD Tear	mN	1000	1115	1300	ISO 1974

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership
Specialty Paper Group

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250