



Polar[®] Liner

Bleached lightweight calendered linerboard for corrugated box converters. Using premium northern fibres and innovative manufacturing technology, Canfor Pulp Limited Partnership products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C
Nominal Basis Weight (g/m²)

Brightness: 82% ISO

	<i>units of measure</i>	80	125	146	150	<i>Test Method</i>
Moisture	%	6.5	6.5	6.5	6.5	-
Ring Crush	<i>kN/m</i>	1.0	1.4	2	2.2	ISO 12192
SCT	<i>kN/m</i>	2.2	3.3	3.7	3.9	ISO 9895
Porosity	<i>Gurley</i>	25	25	25	25	ISO 5636
Cobb – 2 minute	<i>gsm</i>	30	30	30	30	TAPPI T441
Smoothness	<i>Sheffield</i>	285	310	345	350	ISO 8791
Burst	<i>kPa</i>	355	660	790	750	ISO 27585
Caliper	<i>mm</i>	0.11	0.17	0.19	0.20	TAPPI T411

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership
Specialty Paper Group

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250