



# Polar<sup>®</sup> Yellow Kraft

Canfor Pulp Limited Partnership's Polar<sup>®</sup> Yellow Kraft is a high performance paper with balanced TEA, enabling the sheet to resist rupturing forces regardless of direction. This paper has the excellent runnability characteristics of Canfor Pulp Limited Partnership's high performance paper. Canfor Pulp Limited Partnership paper is made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

## TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C  
Nominal Basis Weight (g/m<sup>2</sup>)

	<i>units of measure</i>	<b>90</b>	<i>Test Method</i>
<b>MD TEA</b>	<i>J/m<sup>2</sup></i>	<b>234</b>	<i>ISO 1924-2</i>
<b>CD TEA</b>	<i>J/m<sup>2</sup></i>	<b>278</b>	<i>ISO 1924-2</i>
<b>MD TEA Index</b>	<i>J/g</i>	<b>2.6</b>	<i>ISO 1924-2</i>
<b>CD TEA Index</b>	<i>J/g</i>	<b>3.1</b>	<i>ISO 1924-2</i>
<b>MD Tensile</b>	<i>kN/m</i>	<b>5.5</b>	<i>ISO 1924-2</i>
<b>CD Tensile</b>	<i>kN/m</i>	<b>5.4</b>	<i>ISO 1924-2</i>
<b>MD Stretch</b>	<i>%</i>	<b>6.5</b>	<i>ISO 1924-2</i>
<b>CD Stretch</b>	<i>%</i>	<b>8.0</b>	<i>ISO 1924-2</i>
<b>Porosity</b>	<i>s/100mL</i>	<b>14</b>	<i>ISO 5636-5</i>
<b>MD Tear</b>	<i>mN</i>	<b>1515</b>	<i>ISO 1974</i>
<b>CD Tear</b>	<i>mN</i>	<b>1435</b>	<i>ISO 1974</i>

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership  
Specialty Paper Group

100 – 1700 West 75th Avenue,  
Vancouver, British Columbia, Canada V6P 6G2  
Telephone: 604-661-5272 Fax: 604-661-5226  
canforpaper@canfor.com  
www.kodiakpolar.com  
www.canforpulp.com



**820A Guy Street, Kelowna, BC**  
Canada V1Y 7R5  
Telephone: (250) 870-5250