



Kodiak[®] X

A strong unbleached high performance uncalendered paper designed for high conversion rate into multiwall bags. Using premium northern fibres and innovative manufacturing technology, Canfor products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment..

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C
Nominal Basis Weight (g/m²)

	<i>units of measure</i>	70	80	85	90	95	98	<i>Test Method</i>
MD TEA	<i>J/m²</i>	199	224	220	245	250	267	ISO 1924-2
CD TEA	<i>J/m²</i>	197	221	255	247	285	257	ISO 1924-2
MD TEA Index	<i>J/g</i>	2.8	2.8	2.6	2.7	2.6	2.7	ISO 1924-2
CD TEA Index	<i>J/g</i>	2.8	2.8	3.0	2.7	3.0	2.6	ISO 1924-2
MD Tensile	<i>kN/m</i>	4.9	5.7	6.1	6.2	6.8	6.4	ISO 1924-2
CD Tensile	<i>kN/m</i>	4.2	4.6	4.7	5.4	5.3	5.8	ISO 1924-2
MD Stretch	<i>%</i>	6.2	6.0	6.2	5.9	6.5	6.1	ISO 1924-2
CD Stretch	<i>%</i>	7.3	7.3	7.5	7.0	7.5	5.7	ISO 1924-2
Porosity	<i>s/100mL</i>	15	14	15	14	15	12	ISO 5636-5
MD Tear	<i>mN</i>	970	1150	1275	1300	1425	1385	ISO 1974
CD Tear	<i>mN</i>	1035	1245	1335	1380	1490	1490	ISO 1974

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership
Specialty Paper Group

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250