



## Kodiak<sup>®</sup> Bale Wrap

A strong, unbleached, extensible, uncalendered high performance paper designed for pulp bale wrap. Using premium northern fibres and innovative manufacturing technology, Canfor products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment. Also available in a non-extensible grade. Contact Premium 1 Papers for more information.

### TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C  
Nominal Basis Weight (g/m<sup>2</sup>)

	<i>units of measure</i>	<b>155</b>	<i>Test Method</i>
<b>MD TEA</b>	<i>J/m<sup>2</sup></i>	<b>446</b>	<b>ISO 1924-2</b>
<b>CD TEA</b>	<i>J/m<sup>2</sup></i>	<b>359</b>	<b>ISO 1924-2</b>
<b>MD Tensile</b>	<i>kN/.m</i>	<b>11.1</b>	<b>ISO 1924-2</b>
<b>CD Tensile</b>	<i>kN/.m</i>	<b>8.9</b>	<b>ISO 1924-2</b>
<b>MD Stretch</b>	<i>%</i>	<b>6.0</b>	<b>ISO 1924-2</b>
<b>CD Stretch</b>	<i>%</i>	<b>5.8</b>	<b>ISO 1924-2</b>
<b>MD Tear</b>	<i>mN</i>	<b>2335</b>	<b>ISO 1974</b>
<b>CD Tear</b>	<i>mN</i>	<b>2310</b>	<b>ISO 1974</b>

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership  
Specialty Paper Group

100 – 1700 West 75th Avenue,  
Vancouver, British Columbia, Canada V6P 6G2  
Telephone: 604-661-5272 Fax: 604-661-5226  
canforpaper@canfor.com  
www.kodiakpolar.com  
www.canforpulp.com



**820A Guy Street, Kelowna, BC**  
Canada V1Y 7R5  
Telephone: (250) 870-5250