



Kodiak® “R”

Unbleached high performance uncalendered paper, with the stiffness needed for high conversion rate into multiwall bags. Kodiak “R” is recommended for applications demanding high CD strength and superior converting runnability.

Using premium northern fibres and innovative manufacturing technology, Canfor Pulp Limited Partnership products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C

Nominal Basis Weight (lb/3000 sqft)

	<i>units of measure</i>	43	50	55	60	65	70	80	<i>Test Method</i>
MD TEA	<i>ft.lbs/ft²</i>	6.7	7.7	8.8	10.3	11.1	12.1	14.3	ISO 1924-2
CD TEA	<i>ft.lbs/ft²</i>	13.0	16.2	17.1	18.0	20.1	21.2	22.3	ISO 1924-2
MD TEA Index	<i>J/g</i>	1.4	1.4	1.4	1.5	1.5	1.5	1.6	ISO 1924-2
CD TEA Index	<i>J/g</i>	2.7	3.0	2.7	2.7	2.8	2.7	2.5	ISO 1924-2
MD Tensile	<i>lbs/in.</i>	36.5	42.3	48.5	53.1	55.4	61.1	66.2	ISO 1924-2
CD Tensile	<i>lbs/in.</i>	24.0	29.7	32.0	34.3	37.1	42.8	41.7	ISO 1924-2
MD Stretch	<i>%</i>	2.3	2.4	2.4	2.6	2.6	2.6	2.5	ISO 1924-2
CD Stretch	<i>%</i>	7.0	7.0	6.7	6.6	6.8	6.2	6.5	ISO 1924-2
Porosity	<i>s/100mL</i>	18	18	16	17	16	17	18	ISO 5636-5
MD Tear	<i>g</i>	94	100	110	119	129	136	194	ISO 1974
CD Tear	<i>g</i>	89	95	108	122	130	140	184	ISO 1974

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership
Specialty Paper Group

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250