



# Polar Liner

Bleached lightweight calendared linerboard for corrugated box converters. Using premium northern fibres and innovative manufacturing technology, Canfor Pulp Limited Partnership products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

## TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C  
Nominal Basis Weight (lb/1000 sqft)

Brightness: 82% ISO

	<i>units of measure</i>	17	26	30	31	<i>Test Method</i>
<b>Moisture</b>	%	6.5	6.5	6.5	6.5	On-line scanner
<b>Ring Crush</b>	<i>lbf/6in.</i>	34.3	48.0	68.5	75.4	ISO 12192
<b>SCT</b>	<i>lbf/in.</i>	12.6	18.8	21.1	22.3	ISO 9895
<b>Porosity</b>	<i>Gurley</i>	25	25	25	25	ISO 5636
<b>Cobb – 2 minute</b>	<i>gsm</i>	30	30	30	30	TAPPI T441
<b>Smoothness</b>	<i>Sheffield</i>	285	310	345	350	ISO 8791
<b>Burst</b>	<i>psi</i>	51	96	115	109	ISO 27585
<b>Caliper</b>	<i>in.</i>	0.0043	0.0067	0.0075	0.0079	TAPPI T411

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership  
Specialty Paper Group

100 – 1700 West 75th Avenue,  
Vancouver, British Columbia, Canada V6P 6G2  
Telephone: 604-661-5272 Fax: 604-661-5226  
canforpaper@canfor.com  
www.kodiakpolar.com  
www.canforpulp.com



820A Guy Street, Kelowna, BC  
Canada V1Y 7R5  
Telephone: (250) 870-5250