



Bleached Tape/Laminating Kraft

A strong, bright and calendered bleached kraft made using premium northern fibres and advanced manufacturing technology. The smooth surface is good for laminating or printing. This grade is especially suited for freezer paper and gumming applications. Canfor Pulp Limited Partnership paper is made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C
Nominal Basis Weight (lb/3000 sq ft)

Brightness: 82% ISO

	<i>units of measure</i>	30	35	40	46	50	55	<i>Test Method</i>
MD TEA	<i>ft.lbs/ft²</i>	3.9	4.9	5.8	6.9	7.3	8.3	<i>ISO 1924-2</i>
CD TEA	<i>ft.lbs/ft²</i>	8.0	9.7	10.9	12.6	13.4	14.0	<i>ISO 1924-2</i>
MD Tensile	<i>lbs/in.</i>	27.4	31.4	36.0	41.1	44.0	48.0	<i>ISO 1924-2</i>
CD Tensile	<i>lbs/in.</i>	16.6	20.6	22.8	27.4	28.6	31.4	<i>ISO 1924-2</i>
MD Stretch	<i>%</i>	1.9	2.1	2.1	2.3	2.2	2.3	<i>ISO 1924-2</i>
CD Stretch	<i>%</i>	6.1	6.1	6.1	6.0	6.0	5.7	<i>ISO 1924-2</i>
Porosity	<i>s/100mL</i>	24	29	25	24	22	22	<i>ISO 5636-5</i>
MD Tear	<i>g</i>	51	56	65	77	81	96	<i>ISO 1974</i>
CD Tear	<i>g</i>	50	56	66	79	83	102	<i>ISO 1974</i>

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership
Specialty Paper Group

100 – 1700 West 75th Avenue,
Vancouver, British Columbia, Canada V6P 6G2
Telephone: 604-661-5272 Fax: 604-661-5226
canforpaper@canfor.com
www.kodiakpolar.com
www.canforpulp.com



820A Guy Street, Kelowna, BC
Canada V1Y 7R5
Telephone: (250) 870-5250