



# Unbleached Tape/Laminating Kraft

Made using premium northern fibres and advanced manufacturing technology. High strength and excellent caliper profile makes this the premium calendered sheet for frozen french fry packaging and other high strength calendered applications. Canfor Pulp Limited Partnership paper is made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

## TYPICAL PROPERTIES

Test Conditions: 50% RH, 23°C  
Nominal Basis Weight (lb/3000 sq ft)

	<i>units of measure</i>	<b>35</b>	<b>39</b>	<i>Test Method</i>
<b>MD TEA</b>	<i>ft.lbs/ft<sup>2</sup></i>	<b>4.7</b>	<b>5.8</b>	<b>ISO 1924-2</b>
<b>CD TEA</b>	<i>ft.lbs/ft<sup>2</sup></i>	<b>9.3</b>	<b>9.6</b>	<b>ISO 1924-2</b>
<b>MD Tensile</b>	<i>lbs/in.</i>	<b>33.7</b>	<b>38.3</b>	<b>ISO 1924-2</b>
<b>CD Tensile</b>	<i>lbs/in.</i>	<b>20.6</b>	<b>22.8</b>	<b>ISO 1924-2</b>
<b>MD Stretch</b>	<i>%</i>	<b>1.9</b>	<b>2.1</b>	<b>ISO 1924-2</b>
<b>CD Stretch</b>	<i>%</i>	<b>5.8</b>	<b>5.4</b>	<b>ISO 1924-2</b>
<b>Porosity</b>	<i>s/100mL</i>	<b>32</b>	<b>30</b>	<b>ISO 5636-5</b>
<b>MD Tear</b>	<i>g</i>	<b>49</b>	<b>46</b>	<b>ISO 1974</b>
<b>CD Tear</b>	<i>g</i>	<b>51</b>	<b>48</b>	<b>ISO 1974</b>

Subject to order run minimums.

CPLP paper is produced by CPLP and marketed worldwide by Premium 1 Papers:



Canfor Pulp Limited Partnership  
Specialty Paper Group

100 – 1700 West 75th Avenue,  
Vancouver, British Columbia, Canada V6P 6G2  
Telephone: 604-661-5272 Fax: 604-661-5226  
canforpaper@canfor.com  
www.kodiakpolar.com  
www.canforpulp.com



820A Guy Street, Kelowna, BC  
Canada V1Y 7R5  
Telephone: (250) 870-5250